

Standart waxes						
Product	Melting point (°C)	Oil content (%)	Penetration	Colour	Shape	
Paraffin G3	57-60	0.7-1%	13-20	white	slabs	
Paraffin G2	55-57	0.7-1%	13-20	white	slabs	
Paraffin G3L	57-60	1.5%max	30 max	white	slabs	
Paraffin London	50-54	4-7%	25-35	yellowish	slabs	
Paraffin M4	62-66	1.5 %max	15-24	white	slabs	
Paraffin M5	52-54	0.5%max	25 max	white	slabs	
Paraffin M6	56-58	0.5% max	20 max	white	slabs	
Paraffin Cyclon	56	0.8%	8	yellowish	slabs	
Paraffin M7	54-56	0.5% max	20 max	white	slabs	
Paraffin M8	57-59	0.75%max	12-17	white	slabs	

Paraffin M9	58-60	0.5%max	20 max	white	slabs	
Paraffin M10	60-62	0.5%max	20 max	white	slabs	
Granulated Paraffin C1	57-60	0.7-1%	13-20	white	granules	
Granulated Paraffin F1	50-54	1-1.5%	28-30	white	granules	
Granulated Paraffin H1	57-60	0.7-1%	13-20	White	granules	

Stearic acid						
Product	Melting point (°C)	Acid value	Iodine value	Colour	Shape	
Stearic acid F1	58-60	201-205	Max 0.5	White	flakes	
Stearic acid C1	54-57	207-212	Max 0.5	White	flakes	